Shandong Zhuoxing Chemical Co., Ltd.
Zibo Zhuoxing Enterprises Co., Ltd.

Slump Retention Type PCE Powder

Advantages/Characteristics:

1) Slump Retention Type PCE Powder with solid content : 97% min. Slump Retention Type PCE Powder is an admixture to delay the hydration heat release rate, lower the ceiling temperature and decrease the cracks of thermal stress caused by concentrated heat release.

2) With a high slump retention ability, enhence cohesion, without concrete or mortar segregation.

3) With a good dispersion, an excellent adaptability to different cements, and good water-reducing properties.

4) Having a good thermostability to 300℃ (one hundred degree celsius centigrade).

Usages and Cautions:

(1) A recommended dosage is 0.1%-0.8% by the weight of cementitious materials. Actual dosages should be determined by mixture design test according to concrete strength grade.

(2) Concrete test must be carried out before utilization.

(3) Slump Retention Type PCE Powder is forbidden to be mixed with naphthalene sulphonate.

Mobile/Wechat:0086 13053363281,0086 17865273019
Mail:sales@zhuoxingchem.com,sales02@zhuoxingchem.com
Web site:https://www.sdzhuoxingpce.com,www.zhuoxingchem.com

(4) Compatibility test must be done when it is used together with other admixtures.

Package: Packed in 25kg plastic woven bags with PE inner liner, 16 mt with pallets loaded in one 20’ GP, 27 mt with pallets loaded in 40’ HQ by sea, 25.5 mt with pallets loaded in 40’ HQ by train

Shelf time: 12 months.

Application:

1. It is used for gypsum based and cement based dry mix mortar.

It can also be used for oil well cementing operation.

2. It is especially for cementitious self-levelling underlayments (SLU), plasters and masonry, non-shrink grouts, self-levelling floor screeds, repair mortars, injection mortars, dry mix concrete, tiles adhesives and joint fillers.

Item	Unit	Standard
Appearance	/	White or light yellow powder
Density	kg/m3	500±50
pH (23℃)	/	6.0±1.0
Solid Content	%	97.0±1.0
Moisture	%	≤3.0

Mobile/Wechat:0086 13053363281,0086 17865273019
Mail:sales@zhuoxingchem.com,sales02@zhuoxingchem.com
Web site:https://www.sdzhuoxingpce.com,www.zhuoxingchem.com

content		
Water Reducing Ratio	%	⩾22
Cl-	%	⩽0.02
Alkali content	%	⩽0.3



Contact information:

Shelly Cui

The seller: Zibo Zhuoxing Enterprises Co., Ltd.

Add: Room 1103, 11th Floor, Yunlong Plaza B, No.28 Huaguang Road, Zhangdian District, Zibo City , Shandong Province, China

Mobile/Wechat:0086 13053363281,0086 17865273019

Mail:sales@zhuoxingchem.com,sales02@zhuoxingchem.com

Web site:https://www.sdzhuoxingpce.com,www.zhuoxingchem.com

Shandong Zhuoxing Chemical Co., Ltd.
Zibo Zhuoxing Enterprises Co., Ltd.

255000

Manufacturer: Shandong Zhuoxing Chemical Co., Ltd.

Add: Xinhai Industrial Zone, Wudi County, Binzhou City, Shandong Province, China

Tel/Fax: 0086 533 2284032

Mobile/ Wechat: 0086 13053363281, 0086 18615126163

Skype:cui.shelly

Mail:sales@zhuoxingchem.com shellypce@hotmail.com

Web site:www.zhuoxingchem.com

http://sdzhuoxing.en.alibaba.com